

BCR

RED line refinishing



Related products

341 BCR UNI Putty

2-component universal polyester putty.

Designed for smoothing surfaces with damage up to 5 mm deep. It is characterized by good elasticity. The putty is easy to apply and sand. Can be used on many types of metal surfaces.

Color
Yellow



Use suitable
respiratory
protection



Degreaser



100:2

4-6 min – 20°C



30-40 min
– 20°C



P80-P240



2004/42/EC
(250g/l) 247 g/l

Art. No.	Product name	Content	Pack. un.
109507	341 Uni Putty	0,5kg	18
109031	341 Uni Putty	1 kg	12
109032	341 Uni Putty	1,8 kg	12
109583	341 Uni Putty	4 kg	4

Related products

- **PBO Hardener**
Peroxide hardener for polyester resins



Technical information

Version 3.0.
02/2021

341 BCR Uni Putty

2-component polyester putty is used for smoothing surfaces with damage up to 5 mm deep. It is characterized by good elasticity. The putty is easy to apply and sand. Can be used on many types of metal surfaces.

Additional components

Hardener PBO - peroxide hardener for polyester resins

RULES FOR WORKING WITH THE PRODUCT

Surface preparation and cleaning



Substrate: metals (steel, aluminum, electrolytic zinc coating) and polyester surfaces.

metals should be well degreased and sanded;


Polyester surface must be cleaned, degreased and sanded.

After sanding, remove all contaminants from the surface, including sanding products. Before priming it is necessary to degrease the surface.

Product use




Use personal respiratory protection



Drying at 20 °C

30-40 min




Mixing products:

100: 2



IR - drying:

Use as recommended by the equipment
manufacturer. Drying time -5 min T max -80 ° C



Pot life of the mixture at 20 ° C:

4-6 min



P80-P240

Product properties



SCRATCH RESISTANT

2004/42 / EC
(250g / l) 247 g / l

Density at 20 ° C: **1.85 kg / l**

Colors: **yellow**

Warranty period in unopened original packaging:

12 months from the date of manufacture.

Additional terms



When using necessary to provide safety. Avoid contact with skin and eyes. Work only in well ventilated areas. When working, use personal protective equipment for the respiratory system.



Store in a ventilated room at temperatures from + 5 ° C to +30 C, do not expose to freezing and direct sunlight.

NOTE:

Do not add more hardener than indicated in the instructions.
Mix thoroughly.

Finishing coats are not applied directly to the putty!

Do not apply on thermoplastic coatings and wash primers!

Do not use putty after the pot life has expired, do not dilute the thickened material.

When special strength and surface protection is required, apply on epoxy primer.

Polyester putties do not harden at temperatures below + 5 ° C...

All data is provided for informational purposes only. This information is based on manufacturer's laboratory tests. Anyone using this product without being guided by this technical documentation does so at their own risk. In this case, the manufacturer company is not responsible for the effectiveness of the product and for any damage incurred as a result of improper use. Film thickness, drying temperature and room humidity can affect the drying time of the product. The manufacturing company is constantly improving its products and their technical characteristics.